

PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁶ : A61K 33/04, 33/24, 31/10, 31/715, 31/765, 31/775, 31/78, 31/785 // (A61K 33/04, 31:10, 31:715, 31:765, 31:775, 31:78, 31:785) (A61K 33/24, 31:10, 31:715, 31:765, 31:775, 31:78, 31:785)</p>	<p>A1</p>	<p>(11) International Publication Number: WO 97/45131 (43) International Publication Date: 4 December 1997 (04.12.97)</p>
<p>(21) International Application Number: PCT/US97/07055 (22) International Filing Date: 25 April 1997 (25.04.97) (30) Priority Data: 08/655,822 31 May 1996 (31.05.96) US 08/802,252 19 February 1997 (19.02.97) US (71) Applicant (for all designated States except US): MICRO THERAPEUTICS, INC. [US/US]; 1062-F Calle Negocio, San Clemente, CA 92673 (US). (72) Inventors; and (75) Inventors/Applicants (for US only): EVANS, Scott [US/US]; 1252 Country Hills Drive, Santa Ana, CA 92705 (US). GREFF, Richard, J. [US/US]; 2891 Alton Drive, St. Pete Beach, FL 33706 (US). WRIGHT, James, I. [US/US]; 19142 Mesa Drive, Villa Park, CA 92681 (US). (74) Agents: KREBS, Robert, E. et al.; Burns, Doane, Swecker & Mathis, L.L.P., P.O. Box 1404, Alexandria, VA 22313-1404 (US).</p>		<p>(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, HU, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, TJ, TM, TR, TT, UA, UG, US, UZ, VN, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published With international search report.</p>
<p>(54) Title: COMPOSITIONS FOR USE IN EMBOLIZING BLOOD VESSELS (57) Abstract Disclosed are compositions suitable for use in embolizing blood vessels which compositions comprise a polymer, a biocompatible solvent and a contrast agent. The polymer is selected from the group consisting of polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and copolymers of styrene/maleic acid.</p>		

Best Available Copy

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LJ	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

COMPOSITIONS FOR USE IN EMBOLIZING BLOOD VESSELS

5 BACKGROUND OF THE INVENTION

Field of the Invention

This invention is directed to novel compositions suitable for use in embolizing blood vessels. In particular, this invention is directed to embolizing compositions comprising a biocompatible polymer, a biocompatible solvent and a contrasting agent. The compositions of this invention find particular utility in embolizing blood vessels in, for example, the treatment of aneurysms and in ablating diseased tissues.

15 References

The following publications are cited in this application as superscript numbers:

- 1 Mandai, et al., "Direct Thrombosis of Aneurysms with Cellulose Acetate Polymer", *J. Neurosurg.*, 77:497-500 (1992)
- 20 2 Kinugasa, et al., "Direct Thrombosis of Aneurysms with Cellulose Acetate Polymer", *J. Neurosurg.*, 77:501-507 (1992)
- 25 3 Greff, et al., *U.S. Patent Application Serial No. 08/508,248*, for "Cellulose Diacetate Compositions for Use in Embolizing Blood Vessels", filed July 27, 1995.
- 30 4 Greff, et al., *U.S. Patent Application Serial No. 08/507,863*, for "Novel Compositions for Use in Embolizing Blood Vessels", filed July 27, 1995.
- 35 5 Evans, et al., *U.S. Patent Application Serial No. 08/____*, for "Methods for the Reversible Sterilization of Male Mammals, filed concurrently herewith as Attorney Docket No. 018413-007
- 6 Evans, et al., *U.S. Patent Application Serial No. 08/____*, for "Methods for the Reversible Sterilization of Female Mammals, filed concurrently herewith as Attorney Docket No. 018413-014

All of the above references are herein incorporated by reference in their entirety to the same extent as if each individual reference was specifically and individually indicated to be incorporated herein by reference in its entirety.

5 State of the Art

It is desirable in many clinical situations to embolize blood vessels to prevent/control bleeding (e.g., organ bleeding, gastrointestinal bleeding, vascular bleeding, bleeding associated with an aneurysm) or to ablate diseased tissue (e.g., tumors, etc.). Embolization of blood vessels has heretofore
10 employed certain polymer compositions and particulates, e.g., silicone, metallic coils, sclerosing materials and the like. Because of their ease in delivery, water insoluble non-biodegradable polymers such as cellulose acetate^{1,2,3} or ethylene vinyl alcohol⁴ dissolved in, for example, DMSO have been employed to embolize blood vessels. These compositions are delivered to the vascular site to
15 be embolized by, for example, a catheter or a syringe. Typically, these compositions will comprise a contrast agent to facilitate guidance of the catheter or syringe to the vascular site as well as the placement of the polymer precipitate which embolizes the blood vessel. Upon contact with the aqueous blood environment at this vascular site, the DMSO dissipates away from the
20 insoluble polymer which results in polymer precipitation and embolization of the blood vessel.

In addition to use in embolizing blood vessels, these compositions can also be employed in the reversible sterilization of mammalian males and
25 females.^{5,6} In the former case, the polymer composition is injected into the vas deferens and upon contact with the aqueous fluid therein, precipitates to block the vas. In the latter case, the polymer composition is injected into the fallopian tubes and upon contact with the aqueous fluid therein, precipitates to block the tube. In either case, sterilization arising from the blockage can be
30 reversed at a latter date by injecting DMSO into the polymer blockage to remove the polymer.

While progress has been made in the development of compositions which can be employed in such methods, only a limited number of polymers suitable for use in such compositions have been identified. While these polymers minimally meet the criteria for use in these environments, the identity of additional polymers is essential to developing versatile methods utilizing the specific characteristics of each polymer. For example, embolization techniques requiring deep vascular penetration will require a composition having a relatively slow polymer precipitation rate. Contrarily, techniques requiring rapid embolization of, for example, a bleeding aneurysm or a high blood flow vascular site will require a composition having a relatively fast polymer precipitation rate.

In either case, polymers suitable for use in such compositions must meet stringent conditions for use in embolizing blood vessels, in reversible sterilization, etc. Specifically, suitable polymers ideally should be soluble in the biocompatible solvent, be easy to deliver (e.g., low viscosity) via a catheter or a syringe, be compatible with a contrast agent, and the resulting precipitate should form a well defined coherent mass which is non-biodegradable. This last requirement is, of course, essential to use *in vivo* where a coherent mass is critical to either successful embolization or sterilization. Likewise, compatibility with the contrast agent is necessary in order to permit monitoring the *in vivo* injection of the composition and to confirm its presence after the procedure is complete.

SUMMARY OF THE INVENTION

This invention is directed to the discovery of novel polymers which are suitable in compositions useful in *in vivo* applications such as in embolizing blood vessels and/or reversibly sterilizing mammalian patients. Specifically, this invention is directed to the discovery that polymers such as polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and copolymers of styrene/maleic acid can be

employed in combination with a biocompatible solvent and a contrast agent and the resulting compositions are suitable for use in embolizing blood vessels; in reversible sterilization of mammalian patients, etc.

5 Accordingly, in one of its composition aspects, this invention is directed to a composition comprising:

- (a) from about 2.5 to about 8.0 weight percent of a polymer selected from the group consisting of polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and
10 copolymers of styrene/maleic acid, and mixtures thereof;
- (b) from about 10 to about 40 weight percent of a contrast agent;
- (c) from about 52 to about 87.5 weight percent of a biocompatible
solvent

 wherein the weight percent of the polymer, contrast agent and
15 biocompatible solvent is based on the total weight of the complete composition.

In one of its method aspects, this invention is directed to a method for embolizing a blood vessel by injecting into said blood vessel a sufficient amount of a composition comprising:

- 20 (a) from about 2.5 to about 8.0 weight percent of a polymer selected from the group consisting of polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and
copolymers of styrene/maleic acid, and mixtures thereof;
- (b) from about 10 to about 40 weight percent of a contrast agent;
- 25 (c) from about 52 to about 87.5 weight percent of a biocompatible
solvent

 wherein the weight percent of the polymer, contrast agent and
biocompatible solvent is based on the total weight of the complete composition
under conditions wherein a precipitate is formed which embolizes the
30 blood vessel.

In a preferred embodiment, the contrast agent is a water insoluble contrast agent. In still a further preferred embodiment, the biocompatible solvent is dimethylsulfoxide (DMSO).

5 DETAILED DESCRIPTION OF THE INVENTION

This invention is directed to novel compositions comprising specific polymers, a contrast agent and a biocompatible solvent.

Prior to discussing this invention in further detail, the following terms
10 will first be defined:

The term "embolizing" as used in conjunction with "embolizing compositions" and "embolizing agents" refers to a process wherein a material is injected into a blood vessel which thereafter fills or plugs the blood vessel
15 and/or encourages clot formation so that blood flow through the vessel ceases. The embolization of the blood vessel is important in preventing/controlling bleeding (e.g., organ bleeding, gastrointestinal bleeding, vascular bleeding, bleeding associated with an aneurysm) or to ablate diseased tissue (e.g., tumors, etc.) by cutting off its blood supply.

20 The term "contrast agent" refers to a biocompatible (non-toxic) radiopaque material capable of being monitored during injection into a mammalian subject by, for example, radiography. The contrast agent can be either water soluble or water insoluble. Examples of water soluble contrast
25 agents include metrizamide, iopamidol, iothalamate sodium, iodamide sodium, and meglumine. Examples of water insoluble contrast agents include tantalum, tantalum oxide, and barium sulfate, each of which is commercially available in the proper form for *in vivo* use including a particle size of about 10 μ m or less. Other water insoluble contrast agents include gold, tungsten, and platinum
30 powders.

Preferably, the contrast agent is water insoluble (i.e., has a water solubility of less than 0.01 mg/ml at 20°C).

5 The term "biocompatible solvent" refers to an organic material liquid at least at body temperature of the male mammal in which the biocompatible polymer is soluble and, in the amounts used, is substantially non-toxic. Suitable biocompatible solvents include, by way of example, dimethylsulfoxide, analogues/homologues of dimethylsulfoxide, ethanol, acetone, and the like. Aqueous mixtures with the biocompatible solvent can also be employed
10 provided that the amount of water employed is sufficiently small that the dissolved polymer precipitates upon contact with the vas deferens fluid. Preferably, the biocompatible solvent is dimethylsulfoxide.

The term "encapsulation" as used relative to the contrast agent being
15 encapsulated in the precipitate is not meant to infer any physical entrapment of the contrast agent within the precipitate much as a capsule encapsulates a medicament. Rather, this term is used to mean that the contrast agent and copolymer form an integral coherent precipitate which does not separate into a copolymer component and a contrast agent component.

20 The term "hydrocarbyl" refers to organic residues comprising only carbon and hydrogen atoms which residues include, by way of example, alkyl, aryl, alkylaryl, arylalkyl, alkenyl, etc. The hydrocarbyl group typically contains from 1 to 12 carbon atoms.

25

Compositions

The compositions of this invention are prepared by conventional methods whereby each of the components is added and the resulting composition mixed together until the overall composition is substantially homogeneous.
30 Specifically, sufficient amounts of the selected polymer are added to the biocompatible solvent to achieve the effective concentration for the complete

composition. Preferably, the embolizing composition will comprise from about 2.5 to about 8.0 weight percent of the polymer based on the total weight of the composition and more preferably from about 4 to about 5.2 weight percent. If necessary, gentle heating and stirring can be used to effect dissolution of the polymer into the biocompatible solvent, e.g., 12 hours at 50°C.

The polymers suitable for use in this composition include, by way of example, polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and copolymers of styrene/maleic acid, and mixtures of such polymers. Copolymers of urethane/carbonate include polycarbonates that are diol terminated which are then reacted with a diisocyanate such as methylene bisphenyl diisocyanate to provide for the urethane/carbonate copolymers. Likewise, copolymers of styrene/maleic acid refer to copolymers having a ratio of styrene to maleic acid of from about 7:3 to about 3:7.

In any event, the polymers typically will have a molecular weight of at least about 50,000 and more preferably from about 75,000 to about 300,000. In a particularly preferred embodiment, the molecular weight of the polymer can be selected relative to the desired viscosity of the resulting composition. It being understood, of course, that polymers of higher molecular weight will provide for a higher viscosity in the composition as compared to the same polymer having a lower molecular weight.

Sufficient amounts of the contrast agent are then added to the biocompatible solvent to achieve the effective concentration for the complete composition. Preferably, the composition will comprise from about 10 to about 40 weight percent of the contrast agent and more preferably from about 20 to about 40 weight percent and even more preferably 35 weight percent. Insofar as the contrast agent is not soluble in the biocompatible solvent, stirring is employed to effect homogeneity of the resulting suspension. In order to

enhance formation of the suspension, the particle size of the contrast agent is preferably maintained at about 10 μm or less and more preferably at from about 1 to about 5 μm (e.g., an average size of about 2 μm). In one preferred embodiment, the particle size of the contrast agent is prepared, for example, by
5 fractionation. In such an embodiment, a water insoluble contrast agent such as tantalum having a particle size of less than about 20 microns is added to an organic liquid such as ethanol (absolute) preferably in a clean environment. Agitation of the resulting suspension followed by settling for approximately 40 seconds permits the larger particles to settle faster. Removal of the upper
10 portion of the organic liquid followed by separation of the liquid from the particles results in a reduction of the particle size which is confirmed under a microscope. The process is optionally repeated until a desired particle size is reached.

15 The particular order of addition of components to the biocompatible solvent is not critical and stirring of the resulting suspension is conducted as necessary to achieve homogeneity of the composition. Preferably, mixing/stirring of the composition is conducted under an anhydrous atmosphere at ambient pressure. The resulting composition is heat sterilized and then
20 stored preferably in sealed amber bottles or vials until needed.

Each of the polymers recited herein is commercially available but can also be prepared by methods well known in the art. For example, polymers are typically prepared by conventional techniques such as radical, thermal, UV, γ
25 irradiation, or electron beam induced polymerization employing, as necessary, a polymerization catalyst or polymerization initiator to provide for the polymer composition. The specific manner of polymerization is not critical and the polymerization techniques employed do not form a part of this invention.

30 In order to maintain solubility in the biocompatible solvent, the polymers described herein are preferably not cross-linked.

Methods

The compositions described above can then be employed in methods for embolizing mammalian blood vessels or for reversible sterilization of mammalian patients. In the case of blood vessel embolization, a sufficient amount of this composition is introduced into the selected blood vessel by conventional means (e.g., injection or catheter delivery under fluoroscopy) so that upon precipitation of the polymer, the blood vessel is embolized. The particular amount of embolizing composition employed is dictated by the total volume of the vasculature to be embolized, the concentration of polymer in the composition, the rate of precipitation (solids formation) of the polymer, etc. Such factors are well within the skill of the art. In the case of the copolymers recited above, the rate of precipitation can be controlled by changing the overall hydrophobicity/hydrophilicity of the polymer with faster precipitation rates being achieved by a more hydrophobic polymer composition. In this regard, increasing the amount of butyrate content (at the expense of the acetate content) in the cellulose acetate butyrate will also increase the hydrophobicity of the polymer.

One particularly preferred method for delivering the embolizing compositions of this invention to the selected vascular site is via a small diameter medical catheter. The particular catheter employed is not critical provided that polymeric catheter components are compatible with the embolizing composition (i.e., the catheter components will not readily degrade in the embolizing composition). In this regard, it is preferred to use polyethylene in the catheter components because of its inertness in the presence of the embolizing composition described herein. Other materials compatible with the embolizing compositions can be readily determined by the skilled artisan and include, for example, other polyolefins, fluoropolymers (e.g., Teflon™), silicone, etc.

30

When delivered by catheter, the injection rate dictates, in part, the form of the precipitate at the vascular site. Specifically, low injection rates of approximately 0.05 to 0.3 cc/minute will provide for a precipitate in the form of a kernel or nodule which is particularly beneficial for site specific embolization because the precipitate forms primarily at the point of injection. Contrarily, high injection rates of about 0.1 to 0.5 or more cc/several seconds (e.g., up to 10 seconds) will provide for a filament like mass projecting downstream from the catheter tip which may be particularly beneficial for providing the embolizing agent deep into the vascular tree. Such procedures are suitable for embolizing tumor masses, organs and arteriovenous malformations (AVM).

When introduced into the vascular site, the biocompatible solvent diffuses rapidly into the blood and a solid precipitate forms which precipitate is the water insoluble polymer with the contrast agent encapsulated therein. Without being limited to any theory, it is believed that initially, a soft gel to spongy solid precipitate forms upon contact with the blood. This precipitate then restricts blood flow, entrapping red cells thereby causing clot embolization of the blood vessel.

Utility

The compositions described herein are useful in embolizing mammalian blood vessels which, in turn, can be used to prevent/control bleeding (e.g., organ bleeding, gastrointestinal bleeding, vascular bleeding, bleeding associated with an aneurysm) or to ablate diseased tissue (e.g., tumors, etc.). Accordingly, these compositions find use in human and other mammalian subjects requiring embolization of blood vessels.

Additionally, these compositions can be used in the reversible sterilization of mammalian patients as described in concurrently filed applications by Evans, et al.^{5,6}.

It is contemplated that these compositions can be employed as a carrier for a compatible pharmaceutically active compound wherein this compound is delivered in vivo for subsequent release. Such compounds include by way of example only antibiotics, anti-inflammatory agents, chemotherapeutic agents, and the like.

The following examples are set forth to illustrate the claimed invention and are not to be construed as a limitation thereof.

10 EXAMPLES

Unless otherwise stated, all temperatures are in degrees Celsius. Also, in these examples, unless otherwise defined below, the abbreviations employed have their generally accepted meaning:

15

20 cc = cubic centimeter
 cps = centipoise
 DMSO = dimethylsulfoxide
 gm = gram
 mL = milliliter
 RT = room temperature

25

Example 1

The purpose of this example is to determine the suitability of different polymers in compositions comprising DMSO and a contrast agent. The tests were conducted as follows:

1. 1.2 grams of a candidate polymer was weighed out and placed into a 20 mL bottle that had a Teflon capliner in the lid.
2. 12.5 mL (13.8 gm) DMSO was added to the bottle containing the candidate polymer and the cap was placed onto the vial tightly.

3. Each of the bottles was placed in a tightly sealed half gallon jar and placed in an oven at 50°C.

4. The bottles were maintained in the oven for approximately 72 hours and thereafter were allowed to cool to RT.

5 5. Once the samples reached RT, they were visually examined to determine if the polymers were soluble in DMSO.

6. The viscosity of each of the soluble polymers was then estimated relative to a 100 cps fluid standard. All viscosities reported are for 20°C.

10 7. Each of the dissolved polymer solutions was drawn into a syringe and then injected into a physiological saline solution through a 20-gauge blunt needle to determine whether a coherent precipitate formed.

In this example, 21 different polymer compositions were evaluated and the results are set forth in Table I below.

TABLE I

	Polymer	Dissolve	Coherent Precipitate	Viscosity (cps)
5	polymethyl methacrylate	YES	YES (brittle)	< 100
	polybutyl methacrylate	PARTIAL	---	---
	poly(acrylic acid- co-maleic acid) Na	NO	---	---
10	polyacrylonitrile	YES	YES (strong)	> 100
	poly(ethylene-co- methacrylic acid) Na	NO	---	---
	poly(acrylamide- co-acrylic acid)	NO	---	---
15	polycarbonate	NO	---	---
	poly(carbonate- urethane)	YES	YES (rubbery)	~ 100
	polyurethane	NO	---	---
20	polyamide (Nylon 6 or 66)	NO	---	---
	poly(ethylene- co-vinyl acetate)	PARTIAL	---	---
	polysulfone	PARTIAL	---	---
	poly(vinylacetate)	YES	YES (weak)	< 100
25	cellulose acetate butyrate	YES	YES (weak)	< 100
	polyester	NO	---	---
	polyester	NO	---	---
	silicone resin	YES	NO (flock)	< 50

5

nitrocellulose	YES	YES (weak)	> 100
poly(styrene-co-maleic acid)	YES	YES (weak)	< 100
poly(vinylpyrrolidone co-vinyl acetate)	YES	NO (liquid)	< 100
poly(methyl vinyl ether-co-maleic acid)	YES	NO (liquid)	> 100

10

The above results indicate that of the 21 polymers tested, only 11 were soluble in DMSO and of the 11 only 8 formed precipitates in the saline solution. Of these 8, the brittleness of the polymethyl methacrylate precludes its use in embolizing compositions. Accordingly only 6 of the polymers tested are suitable for use in this invention. These six polymers were as follows:

15

polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and copolymers of styrene/maleic acid. Certain polymers provide properties which are more advantageous in certain environments over others.

20

Example 3

25

The purpose of this example is to illustrate how an *in vivo* application of the methods of this invention in the sterilization of a male mammal could be accomplished. In this example, a 50 pound male dog is prepared for sterilization using a composition comprising 5.8 weight percent polyacrylonitrile (PAN) and 20 weight percent tantalum in DMSO. This composition is loaded into a syringe having a needle attached thereto. Local procaine anaesthesia is applied to the scrotum area of the subject. The vas deferens of one side is gripped through the skin by a vas-fixation clamp and lifted. The syringe needle is used to puncture the vas in the direction away from the testis. The PAN polymer composition (0.3 cc) is then delivered to the lumen of the vas deferens. The delivery is easily visualized with fluoroscopy due to the presence of a

30

contrast agent in the polymer composition. After delivery, the DMSO in the PAN composition rapidly diffuses and the PAN precipitates in the lumen resulting in a blockage of the vas deferens. After about 5 minutes, the polymer is fully precipitated and the syringe needle is removed from vas.

5

The same procedure is repeated with the other vas deferens of the male subject.

EXAMPLE 4

10 The purpose of this example is to illustrate an *in vivo* embolization using a composition of this invention.

In this example, a 50 pound male hound was prepared for blood vessel embolization using a composition comprising 5.8 weight percent poly(carbonate-urethane), 20 weight percent tantalum in DMSO was loaded into a syringe. Embolization of the left kidney proceeded by placement of a 3F micro catheter into the kidney through a 5F AngioDynamics Headhunter catheter. The catheter was advanced into the renal artery, flushed with contrast agent to identify the location and then flushed with saline, followed by DMSO, followed by 0.3 cc of the composition described above. The composition was quickly injected into the renal artery over several seconds. After delivery of about 0.2 cc of the composition, the upper pole of the kidney was blocked. Delivery of the remaining composition resulted in the entire kidney being embolized.

25 The above results indicate that the compositions of this invention are suitable for *in vivo* embolization of blood vessels in mammalian subjects.

From the foregoing description, various modifications and changes in the composition and method will occur to those skilled in the art. All such modifications coming within the scope of the appended claims are intended to be included therein.

30

WHAT IS CLAIMED IS:

1. A composition comprising:
 - (a) from about 2.5 to about 8.0 weight percent of a polymer selected
5 from the group consisting of polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and copolymers of styrene/maleic acid, and mixtures thereof;
 - (b) from about 10 to about 40 weight percent of a contrast agent;
 - (c) from about 52 to about 87.5 weight percent of a biocompatible
10 solvent.wherein the weight percent of the polymer, contrast agent and biocompatible solvent is based on the total weight of the complete composition.
2. The composition according to Claim 1 wherein said contrast
15 agent is a water insoluble contrast agent.
3. The composition according to Claim 2 wherein said biocompatible solvent is DMSO.
- 20 4. The composition according to Claim 2 wherein said contrast agent is tantalum.
5. The composition according to Claim 2 wherein said contrast agent is tantalum oxide.
25
6. The composition according to Claim 3 wherein said contrast agent is barium sulfate.
7. The composition according to Claim 1 wherein said polymer is
30 polyacrylonitrile.

8. The composition according to Claim 1 wherein said polymer is polyvinylacetate.

5 9. The composition according to Claim 1 wherein said polymer is cellulose acetate butyrate.

10. The composition according to Claim 1 wherein said polymer is nitrocellulose.

10 11. The composition according to Claim 1 wherein said polymer is a copolymer of urethane/carbonate.

12. The composition according to Claim 1 wherein said polymer is a copolymer of styrene/maleic acid.

15

13. A method for embolizing a blood vessel by injecting into said blood vessel a sufficient amount of a composition comprising:

(a) from about 2.5 to about 8.0 weight percent of a polymer selected from the group consisting of polyacrylonitrile, polyvinylacetate, cellulose acetate butyrate, nitrocellulose and copolymers of urethane/carbonate and copolymers of styrene/maleic acid, and mixtures thereof;

20

(b) from about 10 to about 40 weight percent of a contrast agent;

(c) from about 52 to about 87.5 weight percent of a biocompatible solvent

25

wherein the weight percent of the polymer, contrast agent and biocompatible solvent is based on the total weight of the complete composition under conditions wherein a precipitate is formed which embolizes the blood vessel.

30 14. The method according to Claim 13 wherein said contrast agent is a water insoluble contrast agent.

15. The method according to Claim 13 wherein said biocompatible solvent is DMSO.

5 16. The method according to Claim 14 wherein said contrast agent is tantalum.

17. The method according to Claim 14 wherein said contrast agent is tantalum oxide.

10 18. The method according to Claim 14 wherein said contrast agent is barium sulfate.

15 19. The method according to Claim 13 wherein said polymer is polyacrylonitrile.

20. The method according to Claim 13 wherein said polymer is polyvinylacetate.

20 21. The method according to Claim 13 wherein said polymer is cellulose acetate butyrate.

22. The method according to Claim 13 wherein said polymer is nitrocellulose.

25 23. The method according to Claim 13 wherein said polymer is a copolymer of urethane/carbonate.

30 24. The method according to Claim 13 wherein said polymer is a copolymer of styrene/maleic acid.

25. The method according to Claim 13 wherein the embolizing composition is injected into the blood vessel at a rate of about 0.05 to 0.3 cc/minute.

5 26. The method according to Claim 13 wherein the embolizing composition is injected into the blood vessel at a rate of at least 0.6 cc/minute.

10 27. The method according to Claim 26 wherein the injection rate of at least 0.6 cc/minute is employed to form a filament like mass projecting downstream from the catheter tip for embolizing tumor masses, organs and arteriovenous malformations (AVM).

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US 97/07055

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A61K33/04 A61K33/24 A61K31/10 A61K31/715 A61K31/765
A61K31/775 A61K31/78 A61K31/785 //(A61K33/04, 31:10, 31:715, 31:765, 31:775, 31:78, 31:785), (A61K33/24, 31:10, 31:715, 31:765,

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A61K

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	INVEST. RADIOL. (UNITED STATES), vol. 29, no. 8, 1994, pages 746-751, XP002038436 LINK D.P. ET AL: "Hydrogel Embolic Agents" see abstract see page 747, right-hand column, last paragraph	1-27
Y	SURG. NEUROL. (USA), vol. 36, no. 1, 1991, pages 4-11, XP002038437 SU C.-C. ET AL: "Histopathological Studies of a New Liquid Embolization Method Using Estrogen-Alcohol and Polyvinyl Acetate" see page 5, right-hand column "Group 3"	1-27

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

22 August 1997

Date of mailing of the international search report

19. 09. 97

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

Seegert, K

INTERNATIONAL SEARCH REPORT

International Application No.
PCT/US97/07055

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 31:775,31:78,31:785)

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	J. NEUROSURG., vol. 77, 1992, pages 497-500, XP002038215 MANDAI S. ET AL: "Direct Thrombosis of Aneurysms with Cellulose Acetate Polymer" cited in the application see page 497, left-hand column, last paragraph	1-27
Y	--- WO 85 00969 A (SKY POLYMERS) 14 March 1985 see page 4 - page 7 see claims 1-37	1-27
P,X	--- WO 97 04657 A (MICRO THERAPEUTICS INC ;GREFF RICHARD J (US); JONES MICHAEL L (US)) 13 February 1997 see claims 1-46 --- -/-	1-27

☒ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

Date of mailing of the international search report

19. 09. 97

Name and mailing address of the ISA
European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+ 31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+ 31-70) 340-3016

Authorized officer

INTERNATIONAL SEARCH REPORT

International Application No
PCT/US97/07055

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
P,Y	WO 97 04656 A (MICRO THERAPEUTICS INC ;GREFF RICHARD J (US); JONES MICHAEL L (US)) 13 February 1997 see claims 1-15	1-27
P,Y	WO 97 04813 A (MICRO THERAPEUTICS INC ;GREFF RICHARD J (US); JONES MICHAEL L (US)) 13 February 1997 see claims 1-15	1-27

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 97/07055

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 8500969 A	14-03-85	AU 3394884 A DE 3486088 A DE 3486088 T EP 0153407 A JP 60502087 T US 4631188 A	29-03-85 08-04-93 30-09-93 04-09-85 05-12-85 23-12-86
WO 9704657 A	13-02-97	US 5580568 A AU 6604296 A AU 6604396 A WO 9704656 A AU 6639796 A WO 9704813 A	03-12-96 26-02-97 26-02-97 13-02-97 26-02-97 13-02-97
WO 9704656 A	13-02-97	AU 6604296 A AU 6604396 A WO 9704657 A	26-02-97 26-02-97 13-02-97
WO 9704813 A	13-02-97	US 5580568 A AU 6604396 A AU 6639796 A WO 9704657 A	03-12-96 26-02-97 26-02-97 13-02-97

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☒ **BLACK BORDERS**
- ☒ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☒ **GRAY SCALE DOCUMENTS**
- ☒ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.